

## Abstract

0926041-02001  
000230-14092660

A component for a vacuum deposition apparatus comprises a component body and a spray deposit formed on a surface of a component body. A spray deposit has surface roughness in which a mean spacing  $S$  of tops of local peak of profile is in the range from 50 to 150  $\mu\text{m}$ , and distances to a bottom of profile valley line  $R_v$  and to a top of profile peak line are in the ranges from 20 to 70  $\mu\text{m}$ , respectively. Furthermore, a spray deposit has a low hardness coat selected from an Al base spray deposit of Hv 30 (Vickers hardness) or less, a Cu base spray deposit of Hv 100 or less, a Ni base spray deposit of Hv 200 or less, a Ti base spray deposit of Hv 300 or less, a Mo base spray deposit of Hv 300 or less and a W base spray deposit of Hv 500 or less. Such component for a vacuum deposition apparatus may suppress, with stability and effectiveness, peeling of deposition material adhering on a component during deposition. In addition, the number of apparatus cleaning and of exchange of components may be largely reduced. A target comprises a similar spray deposit. A vacuum deposition apparatus is one in which above component for a vacuum deposition apparatus is applied in a holder of a sample to be deposited, a deposition material source holder, a preventive component and so on.